

## 910-01 Penetrating Asphalt Primer

**Physical Properties:** Complies with CGSB 37-GP-9M and ASTM D-41, Type II

-Colour	Black	-Service Temp (coated face)	-30°C to 85°C (-22°F to 185°F)
-Solids by Volume	37% (approx.)	-Application Temp	May be applied at low temperature.
-Weight	0.87 kg/l (approx.) (8.7 lbs./gal.) [7.2 lbs./U.S. gal.]	-Flammability	Wet Dry
-Coverage	2-10 m <sup>2</sup> /l (100 to 500 ft <sup>2</sup> /gal.) depending on porosity of surface.		Combustible Burns
-Drying Time	@ 50% R.H. 20°C Dry Substrate		
Touch Dry	One hour		
Firm Dry	8 to 24 hours		

### Description

**Bakor 910-01** is a quality penetrating primer of thin brush or spray consistency.

### Uses

For priming and sealing dusty, absorbent surfaces to improve bonding of asphalt coatings and finishes. Used for priming thermal insulation, concrete, masonry, gypsum, asbestos, asphalt roofing felts and similar surfaces.

**Bakor 910-01** can be used with **Blueskin TG**.

### Limitations

Avoid use where solvent odours may taint food or other susceptible products. Do not apply over coal-tar coatings. Do not apply to wet surfaces

### Preparation

Surfaces must be dry and free from dust, dirt, grease and other foreign matter.

### Application

Apply by brush, roller or spray. Protect new work from open flame or adjacent welding activity.

### Clean Up

Use mineral spirits.

### Caution

Contains flammable solvents. Take suitable fire precautions. Do not allow smoking or welding in working area. Keep away from heat and open flame. Use in well-ventilated areas. Keep containers covered when not in use. Harmful if swallowed.