

990-25

Elastomeric Flashing Sheet Unreinforced

Physical Properties

-Colour	Black	-Tear Resistance (ASTM D624)	26 kN/m (150 lbf/in.)
-Specific Gravity	1.42	-Ozone Resistance (ASTM D1149)	No degradation
-Tensile Strength (ASTM D412)	210 kN/m (1200 lbf/in.)	-Water Vapour Transmission (ASTM E96)	per 1.2 mm (0.047 in.) 0.6 ng/Pa.m ² .s (0.01 perms)
Original		-Shore Hardness (ASTM D2240)	70 ± 4 pts.
After 7 days @ 116 °C (240°F)	140 kN/m (800 lbf/in.)		
-Elongation (ASTM D412)	500%		
Original			
After 7 days @ 116°C (240°F)	400%		

Description

990-25 Elastomeric Flashing Sheet is a flexible flashing membrane composed of combination of butyl and EPDM polymers. Compatible with asphalt roofing and waterproofing materials.

Features

- Adheres to roofing and waterproofing asphalts
- Flexible; easy to use
- Elongates to take joint movement
- Strong; high tensile and tear strength
- Excellent exposure capability

Uses

Used in expansion joints and flashing details for hot rubberized asphalt, resaturants and can be used with hot built-up roofing asphalt.

Limitations

Do not expose to petroleum solvents or solvent based roofing products not recommended by **Henry Canada**.

Application

Set **990-25 Elastomeric Flashing Sheet** into hot applied membrane. **790-11, SEBS 890-12** and standard roofing asphalts are acceptable hot applied systems. For cold process systems use **880-11**. Adhesion is enhanced when **990-25** is cleaned with solvents. Alternatively, prime **990-25** using **Bakor 910-01** or **930-18** to improve adhesion. Allow primer to dry.

<>