


COMPLEMENTARY PRODUCTS



PHYSICAL PROPERTIES

HD (type 2) Expanded Polystyrene

Thermal Resistance (ASTM C518 C177) Thickness of 25 mm (1")	RSI-0.73 R-4.17
Vapour Permeability (ASTM E96) Thickness of 25 mm (1")	2.25 perm 130 ng/Pa·s·m ²
Compressive Strength (ASTM D1621) Thickness of 38 mm (1 1/2")	140 kPa 20.31 lbs/in ²
Flexural Strength (ASTM C518 C203) Thickness of 38 mm (1 1/2")	300 kPa 43.71 lbs/in ²
Water Absorption (ASTM D2842) Thickness of 38 mm (1 1/2")	3%
Density (ASTM D1621)	24.02 kg/m³ 1.5 lbs/ft ³
Limiting Oxygen Index (ULC S-701) % minimum	24%
Dimension Stability (ASTM D2126) % max. of linear change	1.5%

DESCRIPTION

Tapered expanded polystyrene insulation board, factory laminated with hot bitumen to a 12.7 mm (1/2") Perlite board, square-end cut, designed to insulate flat or low slope roofs. designed to insulate flat or low slope roofs.

CERTIFICATIONS



**MÂITRES
COUVRESSEURS**
Association des
Maitres Couvresseurs
du Québec



LEED

INSTALLATION

1. If adhered with adhesive, refer to the technical data sheet of the adhesive used for application recommendations.
2. Place the panels in close contact, in parallel rows and without deformation or empty space, as indicated in the shop drawing.
3. Fill joints more than 5 mm (3/16").
4. If mechanically attached, use the appropriate LEXCOR LEXGRIP screws and plates. Follow FM recommendations for the number of mechanical fasteners to be used per panel.

ADVANTAGES

Monolithic panel

Up to 8" (203.2mm) thick to meet the required R-Value in one application.

Fast Installation

One step is saved on site since the insulation panel is already laminated to the cover board.

Low Water Absorption

The closed cell walls are waterproof and as such, water can only penetrate in channels located between polystyrene cells that are held together.

High-Dimensional Stability

According to industry standards, EPS is one of the leaders in terms of size maintenance. This helps the system to remain fully waterproof at all times.

Captive Gas; 98% Air and 2% Plastic

This formula has been used for more than 50 years. It does not contain any VOC, CFC's, HCFC's, Formaldehyde or any gas that can impact the ozone layer. Furthermore, this provides the product with premium features including its light weight and the maintenance of R-Value.

Meets High Standards

Helps to reach Novoclimat (in Quebec if applicable), EnergyStar (Ontario and the Maritimes) and R-2000 (Canada) insulation levels.

Continued on back

BIZOLITE

TYPE HD

TAPERED EXPANDED POLYSTYRENE INSULATION BOARD

PHYSICAL PROPERTIES

Perlite Panel

Density (ASTM C209)	225 kg/m³ 14.5 lbs/ft ³
Compressive Strength (ASTM C165) 5% consolidation	414 kPa 60 lbs/in ²
Laminar Tensile Strength (ASTM C209)	110 kPa 16 lbs/in ²
Flexural Strength (ASTM C203)	1551 kPa 225 lbs/in ²
Break Load (ASTM C203)	4.54 kg 10 lbs
Moisture Content	2%
Water Absorption (ASTM C209) % by vol. max.	3.5%
Installation Linear Expansion (ASTM C209) % max	0.5%



PRODUCT WARRANTY

Thermal Value is 100% Guaranteed

The thermal resistance of the product is 100% guaranteed free of charge for a period of at least 40 years.

SIZES

Width x Length*	1,219 mm x 1,219 mm 48" x 48"
Thickness	51 mm to 305 mm 2" to 12"
Shiplap	16 mm 5/8"
Number of Panels per Skid	Varies according to thickness

*Other sizes available on special order

