

ROOFING

198 Asphalt Roof Resaturant



Read Safety Data Sheet before using this product.

DESCRIPTION: 198 Asphalt Roof Resaturant is a carefully prepared blend of selected asphalt, mineral fillers and selected penetrating oils. These penetrating oils soak into the existing roof mat to help rejuvenate the old asphalt. In addition, a thick layer of asphalt remains on the surface of the roof to protect it from the ultra-violet rays of the sun as well as serving as a binder for the replacement of the gravel or slag.

USES: 198 Asphalt Resaturant may be used as a protective coating for asphalt and gravel roofs.

SURFACE PREPARATIONS: Remove all loose gravel, dirt and dust from the roof by sweeping or power-brooming. If existing gravel is to be reused, it must be washed free of silt. Repair all blisters, breaks or holes in the roof with 19 Ultra Rubberized Flashing Cement and 34 Asphalt Cotton Fabric, 31 Fiberglass Membrane or #5540 Resat-Mat.

APPLICATION: Apply 198 Asphalt Roof Resaturant with a wide, fiber brush or airless spray equipment or standard mastic pump-type equipment at the rate of 7 to 8 gallons per 100 sq. ft. After application of 198 Asphalt Roof Resaturant is completed, clean, dry gravel should be re-applied at the rate of 400 lbs. per 100 sq. ft. Recommended application temperature is 40°F to 120°F. If applying at temperatures lower than 40°F, the substrate must be free of moisture and/or ice crystals.

COVERAGE RATE: Apply at 7 to 8 gallons per 100 sq. ft.

CAUTION: Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, do not induce vomiting. Call a physician immediately. Keep out of reach of children. Store in a heated room and keep container covered when not in use. Do not thin. Dispose of in an environmentally safe manner. Cover air intakes during application and while drying. For exterior use only.

Cold-process systems and coatings, either emulsion or solvent-based, should only be installed on decks with positive drainage. Per NRCA (National Roofing Contractors Association), "The criteria for judging proper slope for drainage is that there be no evidence of standing water on a deck 48 hours after it stops raining."

PACKAGING: Available in 5-gallon pails and 55-gallon drums.

If further information is needed, contact KARNAK Technical services at 800-526-4236.

PHYSICAL PROPERTIES & SPECIFICATIONS

Weight per Gallon:	8.17 lbs.
Solids by Weight:	72% Nominal
Solids by Volume:	65% Nominal
Color:	Black
Application Temp.:	40°F to 120°F
Service Temp (Cured Film):	15°F to 180°F
VOC Content:	270 g/L MAX

ASTM D4479 Type I

